

SUMMARY TABLE OF OREGON DIMENSION LUMBER GRADES

Reference Dimension	SUMMARY TABLE OF OREGON DIMENSION LUMBER GRADES					
	Defect Type	Criteria	#2 & Better	Stud	#3	
Nominal Width and Thickness	Knots	Max. Permitted Knot Size (Diameter)				
		Quality	SOUND, FIRM, ENCASED, AND PITH KNOTS PERMITTED 	ANY QUALITY 		
		Spacing	WELL SPACED			
	Holes	Max. Size				
		Spacing	MAX. KNOT SIZE ALLOWED ONCE WITHIN 8" SECTION AND SUM OF THE SIZE OF ALL KNOTS IN ANY 8" SECTION NOT TO EXCEED TWICE MAX. KNOT SIZE 			
	Unsound Wood	Size & Spacing		SAME AS LIMITING PROVISION FOR HOLES		
Actual Width and Thickness	Wane	Max. from one Edge				
		Total Wane - Width				
		Total Wane - Thickness				
Nominal Width	Split	Max. Length				
		Shake	End Shake - Through			
Standard Length	Shake not at End			SURFACE SHAKES PERMITTED 		
Actual	Slope of Grain	Deviation from Edge per Length				
Nominal	Warp	Severity	LIGHT (SEE WARP TABLES) 		MEDIUM (SEE WARP TABLES) 	
	Manufacturing	Severity	IMPERFECTIONS PERMITTED UP TO 1/8"			